PRODUCTION AND MOLDED PRODUCT FRO POLYLACTIC ACID COMPOSITION, ITS COMPOSITION

Publication number: JP10176039

1998-06-30 Publication date:

Inventor:

HIRAI YOSHIAKI; HORIKAWA YUKIO; KIMURA YOSHIHARU

KANEBO LTD Applicant:

Classification:

C08K5/07; C08G63/08; C08G63/64; - international:

C08G63/78; C08G63/84;

C08L67/04; C08L101/16;

C08K5/00; C08G63/00;

C08L67/00; C08L101/00; (IPC1-7):

C08G63/08; C08G63/64;

C08G63/78; C08G63/84; C08K5/07;

C08L67/04

- European:

Application number: JP19970110169 19970410

JP19970110169 19970410; Priority number(s):

JP19960297506 19961018

View INPADOC patent family

View list of citing documents

Abstract of JP10176039

PROBLEM TO BE SOLVED: To obtain a polyactic acid composition having high molecular weight and excellent heat stability with a small lowering of molecular polymerization of lactide as a cyclic dimer of lactic acid with the component (ii) by using the component B in an amount of 0.15-4.0mol% based on the lactide as a aluminum at a specific ratio. SOLUTION: This composition contains (A) a polylactic acid-based copolymer as a copolymer of (i) L- and/or D-lactic acid and (ii) a weight in molding and capable of giving a molded product having high strength by containing a specific polylactic acid-based copolymer and tris(acetylacetonato) aliphatic polyesters, lactones, lactams and cyclic carbonates [preferably a copolymer of the component (i) and polyethylene glycol] and (B) tris(acetylacetonato) segment derived from at least one kind of compound selected from the group consisting of polyalkylene glycols, polyhydric alcohols, hydroxycarboxylic acids, aluminum in an amount of 0.075-2.0mol% based on a lactic acid unit of the component A. The component A is obtained by performing melt ring-opening

Data supplied from the esp@cenet database - Worldwide